



## MANNOL Anticor Schwarz 9919

Anticor Schwarz is a high – quality anti-corrosion and anti-graveling agent in the form of an aerosol based on synthetic resins and rubbers. It is intended for processing of external and internal surfaces of a car body, a bottom, wheel arches, wings, aprons, lower surfaces of thresholds of cars, etc. It is suitable for processing the internal surfaces of the hood, doors, and body amplifiers. For professional body repairs, it is used to protect welds from the inside of panels, protect the internal surfaces of new body panels, as well as to process fenders, doors, aprons, hoods, trunks, etc. before installing on the car.

### Properties:

- Reliably protects the body from the negative effects of road salt and deicing reagents, all types of atmospheric effects, corrosion, protects from scratches caused by road surface particles (gravel, crushed stone, etc.);
- Has passivating properties, significantly slowing down the corrosion process that has already begun;
- Forms a strong, smooth, indelible elastic film with tixotropic properties (can be applied in a thick layer without forming smudges and self-leveling, and scratches on it are prone to self-tightening), resistant to mechanical influences, to moisture, salts, acids and alkalis after drying. Does not chip or wear during operation; Effectively penetrates into the smallest crevices, displacing water from cracks, crevices and joints between the body panels forms a waterproof layer;
- Has excellent adhesion – holds securely even on smooth, non-porous surfaces. It does not lose its adhesive properties at extremely high temperatures – it does not peel off and is securely held on a heated surface;
- Neutral to metals, plastics, rubbers and paint coatings;
- Resistant to extremely low temperatures, retains plasticity and does not crack;
- It has sound-proof and anti-vibration properties, significantly reducing road noise and vibrations of body elements, thereby increasing the comfort of driving;
- Dry quickly. The declared properties are acquired after complete drying.

Application: before applying the product, the surface must be thoroughly cleaned of rust, dirt and dust, grease, oil and other organic contaminants. For degreasing, we recommend using 9691 MANNOL Brake Cleaner. For best results, it is recommended to apply the product at room temperature. Shake the balloon well until the balloon inside is released and you can hear its sound. Then continue to shake the balloon for another minute. Hold it upright when spraying and spray in a layer of up to 1.5 mm at a distance of about 20-30 cm from the surface. Resistance to abrasion and corrosion increases with the thickness of the coating. For this reason, the spray process should be repeated once or twice after a short (1-2 minutes) drying time. To obtain a uniform coating and not to leave untreated areas, the spray must be carried

out crosswise. The coating is not subject to further staining.  
Depending on the thickness of the layer and weather conditions, the car is ready to move again in about 2 hours. Final drying takes 12-24 hours.

Attention! After application, clean the valve on the cylinder by spraying head down until only the propellant gas is released!

**Specifications**  
**Approval**  
**Recommendation**